

**FNAH-603 醇酸各色甲板漆****FNAH-603 Alkyd Deck Paints**

| | | | | | |
|---------------------------------|---|--|---------|--|----|
| 产品特性 Characteristics | 良好的耐候性、良好的耐海水性、良好的耐磨性、 Good weather, seawater and abrasion resistance. 附着力极好、干燥快。 Good adhesion, quick drying. | | | | |
| 产品用途 Uses | 主要用于船甲板和水线上层建筑涂装。 For deck and the superstructure above the waterline. | | | | |
| 颜色 Color | 各色 All colors | | | | |
| 施工温度 Application temperature | 5℃~40℃ | 湿度 85%以下 relative humidity below 85% | | | |
| 施工条件 Application method | 无气喷涂 Airless spray | 推荐 Recommended | | | |
| | 喷嘴尺寸 Nozzle tip | 0.4~0.5mm | | | |
| | 压力 Fluid pressure | 100~150kg/cm ² | | | |
| | 稀释比率 Thinning ratio | 0~5% | | | |
| | 适用于无气喷涂、空气喷涂、刷涂及辊涂 May be applied by airless spray, air spray, brush, or roller. | | | | |
| 稀释剂 Thinner | 醇酸稀释剂 Alkyd thinner | | | | |
| 混合比率 Mixing ratio | 单组分 One-pack | | | | |
| 涂装膜厚 Film thickness | 干膜: 30μm/道 | 湿膜: 60μm/道 Wet film thickness: 60μm /coat | | | |
| 固体含量 Solid content | 60% | | | | |
| 比重 Specific gravity | 白色 1.29 | 黑色 1.29 | 绿色 1.30 | 铁红 1.40 White 1.29 Black: 1.29 Green 1.30 Iron Red 1.40 | |
| 涂覆率 Coverage rate | 理论值 : 0.09kg/m ² /30μm 0.07L/m ² /30μm Theoretical: 0.09kg/m ² /30μm 0.07 L/m ² /30μm 实际值 : 与表面处理, 外界环境, 施工方法等多种因素有关。 Actual: depending on the surface treatment, environment and application methods. | | | | |
| 干燥时间 Drying time | 温度 (℃) Temperature (℃) | 5 | 10 | 20 | 30 |
| | 指触干燥 (hrs) Dry to touch (hrs) | 3 | 2 | 1.5 | 1 |
| | 半硬干燥 (hrs) Dry hard (hrs) | 36 | 24 | 18 | 12 |



| | | | | | |
|-------------------------------|--|----|----|----|----|
| 涂装间隔 Coating interval | Min. 最小 (hrs) | 36 | 24 | 18 | 12 |
| | Max. 最大 (hrs) | — | — | — | — |
| 储存期限 Shelf life | 一年 12 months | | | | |
| 包装规格 Packing specification | 20kg/桶 20 kg/barrel | | | | |
| 表面处理 Surface preparation | 配套底漆表面应清洁干燥，无污物。 The preceding primer surface must be clean, dry and free of contaminants. 注意施工与底漆的涂装间隔。 Pay attention to the coating interval to the primer. | | | | |
| 适用底材 Substrate: | 裸钢 Bare steel | | | | |
| 适用下涂 Primer coat: | 醇酸防腐底漆或参考我公司配套 Alkyd Anticorrosive Primer, or refer to our system. | | | | |
| 安全注意事项 Safety Precautions | 任何油漆施工中均应保证提供以下措施: The following shall be guaranteed during any paint applications: 避免接触皮肤和眼睛。 Avoid skin and eye contact. 如果油漆接触到皮肤或眼睛，应用大量水冲洗并立即就医。 In case of skin or eye contact, flush with large amount of water and immediately get medical attention. 保证良好的通风。 Assure well-ventilated working place. 小心火灾或爆炸。 Take precautions of the risks of fire or explosion. 现场遵守一切健康安全规定。 Observe all health and safety regulations on site. | | | | |
| 提醒注意 Declaration | 本说明书所提供信息均为目前我方所掌握最全面正确的资料，鉴于产品使用条件非我方所能控制，此中信息不含担保，即仅在选取产品上对买方负责。由于我公司产品及生产工艺的不断发展，此中所有信息均以我方确认为准。 The information given on this technical data sheet is correct to the best of our knowledge. In consideration of the application conditions of the product are beyond our control, so no guarantee is involved herein, namely, we are responsible for the buyers only in terms of their selecting a product. All data must be clarified from our company because of the constantly improvement of our product and its manufacturing process. | | | | |