

FXHG-309 游艇船底防污漆 (游艇专用)

FXHG-309 Antifouling Paint for Yacht Bottom

产品特性 Characteristics 由硅烷改性环氧树脂为基料,具有极好的耐水性及憎水性,耐候性及防腐性异常优异

Silane-modified epoxy resin as binder, wonderful water resistance and hydrophobicity, and excellent

weather and corrosion resistance.

对酸碱盐有非常好的耐受性, 耐磨性优异

Very good resistance to acid, alkali and salt, and excellent abrasion resistance.

硬度高,对海生物的附着具有排斥性

High hardness with repellency to attachment of marine growths

产品用途

主要用于游艇船底的防污及螺旋桨的防锈,也可作为海洋产品的养殖设施的防污使用。

Mainly used for antifouling of yacht bottom and antirust of propeller, also used for antifouling of

farming facilities of marine products.

颜 色

铁红色

Color

Uses

Iron red

施工条件

无气喷涂 airless spray

推荐 recommend

Application conditions

喷嘴尺寸 nozzle size

0.4~0.5mm 100~150kg/cm²

压力 pressure 稀释比率 dilution ratio

0~5% by wet. (重量比)

适用于常规的喷涂、刷涂和辊涂

May be applied by spray, brush, or roller

稀释剂

专用稀释剂

Thinner

Special thinner

混合比率

双组分: 主剂/固化剂=4/1(重量比)

Mixing ratio

Two components: base/hardener=4:1 by weight

涂装膜厚

干膜: 120µm/道

湿膜:200μm/道

Film thickness

Dry film thickness 120µm/coat

wet film: 200µm /coat

固体含量

Solid content

%

比 重

Specific gravity

涂 覆 率

理论值: 0.188 千克/平方米/120μm

L/平方米/120μm

Coverage rate

Theoretical: $0.188kg/m^2/120\mu m$

 $L/m^2/120\mu m$

实际值:与表面处理、外界环境、施工方法等多种因素有关。

Actual: depending on surface treatment and environment conditions, and application methods.



干燥时间	温度 2	5℃
Drying time	Temperature	
, ,		hrs
	Dry to touch	
	实干: 2	4hrs
	Dry to handle	
涂装间隔	Min. 最小 2	4hrs
Coating interval	Max. 最大	
Λ+ν -/ +Η□ /Γ	v F	
储存期限	半年	
Shelf life	6 months	
包装规格	双组份包装: 25kg 为一组,组份)一为 20kg,组份二为 5kg
Package	2K packaging: 25kg a kit includes Part A 20kg and Part B 5kg	
	用适当的清洁剂和脱脂剂除去油	胎
	Remove oil thoroughly with suitable detergent or degreaser.	
表面处理	用高压空气吹扫除去灰尘的污物	
Surface treatment	Remove the contaminants like dust	t with a high-pressure blower.
	施工前确认表面清洁干燥	
	Confirm the surface clean and dry	before application.
涂装配套	适用底材:金属底材、铝材或玻	·
Coating system	Substrate: metal, aluminum or glass fiber reinforced plastic	
couring by overing	适用下涂: 环氧连接漆	
	Applicable subsequent coat : Epox	y Tie Coat
	任何油漆施工中均应保证提供以	下措施:
	The following shall be guaranteed	
	避免接触皮肤和眼睛。	
	Avoid skin and eye contact.	
	如果油漆接触到皮肤或眼睛,应	
	•	flush with large amount of water and immediately get medical
安全注意事项	attention. 事项保证良好的通风。	
Safety precautions	KIE 医好的进风。 Insure adequate ventilation in working place.	
Safety precautions	小心火灾或爆炸。	mig prace.
	Take precautions of the risks of fire	e or explosion.
	现场遵守一切健康安全规定。	
	Observe all health and safety regul	ations on site
	本说明书所提供信息均为目前我	方所掌握最全面正确的资料,鉴于产品使用条件非我方所能控
	制,此中信息不含担保,即仅在选取产品上对买方负责。由于我公司产品及生产工艺的不断发	
	展,此中所有信息均以我方确认为准。	
提醒注意	The information given on this technical data sheet is correct to the best of our knowledge. In	
Declaration	consideration of the application conditions of the product are beyond our control, so no guarantee is	
	involved herein, namely, we are responsible for the buyers only in terms of their selecting a product.	
	All data must be clarified from our	company because of the constantly improvement of our product



and its manufacturing process.