



## FXUH 无溶剂聚氨酯防腐涂料

### FXUH Solvent-Free Polyurethane Anticorrosive Coating

产品特性 Characteristics	具有强度高、延伸率大、耐水性能好。 Strong strength, high elongation rate, good water resistance.			
	性能优异, 使用寿命长, 应用面广。 Excellent performance, long service life, wide range of applications.			
	对基层变形的适应能力强。 Strong ability to adapt to the base deformation.			
产品用途 Uses	可用于各种工程的防水、装饰, 也可用各种运动场地, 池子管道等的防腐, 亦可作为高级地板的嵌缝材料等。 As water-proof or decorative coating for variety of works; as anticorrosive coating for sports facilities, pools and pipelines; as sealing material for high-grade floors.			
颜色 Color	各色 All colors			
施工条件 Equipment	无气喷涂 airless spray	喷嘴尺寸 nozzle orifice	压力 nozzle pressure	稀释比率 thinning ratio
	推荐 recommended	0.5~0.6mm	100~150kg/cm <sup>2</sup>	0
	适用于常规的喷涂、刷涂和辊涂 May be applied by spray, brush, or roller.			
混合比率 Mixing ratio	双组分: 主剂/固化剂=3/1 (重量比) Two component : base /curing agent =7/1 by weight			
混合使用期 Pot life	温度(temperature):	10℃	20℃	30℃
	混合使用期(pot life):			
涂装膜厚 Film thickness	干膜: 1mm/道 Dry film thickness : 1mm/coat			
固体含量 Solid content	98%			
	98%			
比重 Specific gravity	1.3			



---

涂覆率 Coverage rate	理论值 : 1.30 千克/平方米/1mm      L/m <sup>2</sup> /1mm Theoretical: 1.30 kg/m <sup>2</sup> /1mm      L/m <sup>2</sup> /1mm
	实际值: 与表面处理, 外界环境, 施工方法等多种因素有关。 Actual: depending on the surface treatment, environment and application methods.

---

干燥时间 Drying time	温度(temperature)      25 °C 指触干燥(dry to touch)      4 hrs 半硬干燥(dry to semi-hard)      24 hrs
---------------------	---

---

涂装间隔 Coating interval	Min. 最小      24hrs Max. 最大      —      —
--------------------------	---

---

储存期限 Shelf life	一年 12 months
--------------------	-----------------

---

包装规格 Packing	双组份包装: 22.8kg 为一组, 组份一为 20kg, 组份二为 2.8kg 2K packaging: A kit 22kg contains Part A 20kg and Part B 2kg.
-----------------	---

---

表面处理 Surface preparation	底漆表面必须清洁干燥无污物 The primer surface must be clean, dry and free of dirt  依照 SSPC-SP1 溶剂清洗标准除去油脂。 Remove oil thoroughly with suitable detergent in accordance with SSPC-SP1.  用高压空气吹扫除去灰尘等污物。 Remove any contaminants like dust with high pressure blower.  施工前注意与底漆的涂装间隔, 如超过 7 天以上请做拉毛。 Note the coating interval to the primer before application. Do stucco exceeding seven days.
-----------------------------	---

---

涂装配套 Coating system	经过喷砂(抛丸)处理其表面达到 ISOSa2.5 级的裸钢, 如有任何疑问请向津海公司查询。 Bare steel having been sand(shot) blasted to ISOSa2.5. If you have any doubt, please check with our company.
------------------------	--

---

安全注意事项 Safety Precautions	任何油漆施工中均应保证提供以下措施: The following shall be guaranteed during any paint applications: 避免接触皮肤和眼睛。 Avoid skin and eye contact. 如果油漆接触到皮肤或眼睛, 应用大量水冲洗并立即就医。 In case of skin or eye contact, flush with large amount of water and immediately get medical attention.
------------------------------	---

---



---

保证良好的通风。  
Assure well-ventilated working place.  
小心火灾或爆炸。  
Take precautions of the risks of fire or explosion.  
现场遵守一切健康安全规定。  
Observe all health and safety regulations on site

---

提 醒 注 意  
Declaration

本说明书所提供信息均为目前我方所掌握最全面正确的资料，鉴于产品使用条件非我方所能控制，此中信息不含担保，即仅在选取产品上对买方负责。由于我公司产品及生产工艺的不断发展，此中所有信息均以我方确认为准。

The information given on this technical data sheet is correct to the best of our knowledge. In consideration of the application conditions of the product are beyond our control, so no guarantee is involved herein, namely, we are responsible for the buyers only in terms of their selecting a product. All data must be clarified from our company because of the constantly improvement of our product and its manufacturing process.

---